



TEST REPORT

No.:SST16000887

Date.:2016-09-24

Page 1 of 4

Applicant: Benoy Industry CO.LTD

Address: Xiaqiao Village, Dongcheng Town, dongguan City, Guangdong Province ,China

Report on the submitted sample said to be:

Material description: Silicone card holder

Style/ Model No.:	S-pink,S-black,S-gray, S-blue,S-red, S-B	P/O No./ Lot No. :	N/A
Color/ Material:	N/A	Test Request Age :	N/A
Manufactory :	Benoy Industry CO.LTD	Buyer :	N/A
Country of Origin :	China	Country of Export :	USA

Sample received date : September 22,2016

Sample test period : From September 22,2016 to September 24,2016

SUMMARY OF TEST RESULT(S)

Test Item(s)	Conclusion	Remark
Phthalates content - Client's requirement with reference to California Proposition 65	PASS	--
Total lead content - Client's requirement with reference to California Proposition 65	PASS	--

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

Signatories:



John Yue
Lab Manager



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong,China
Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586



TEST REPORT

No.:SST16000887

Date.:2016-09-24

Page 2 of 4

Result:

Phthalates Content - California Proposition 65

Test Method: Sample was extracted with organic solvent, Analysis was performed by Gas Chromatograph Mass Spectrometer(GC-MS).

Client's Limit :	Each < 0.1%
------------------	-------------

Test Item(s)	Unit	Result	
		001+002	003+004+005
Dibutylphthalate(DBP)	mg/kg	ND	ND
Butylbenzylphthalate(BBP)	mg/kg	ND	ND
Di-(2-ethylhexyl)-phthalate(DEHP)	mg/kg	ND	ND
Di-iso-nonylphthalate(DINP)	mg/kg	ND	ND
Di-iso-decylphthalate(DIDP)	mg/kg	ND	ND
Di-n-octylphthalate(DNOP)	mg/kg	ND	ND
Di-n-hexyl phthalate(DnHP)	mg/kg	ND	ND

Note:

ND = Not detected(<DL)

% = percent

1000 mg/kg = 0.1 %

mg/kg = milligram(s) per kilogram

Detection Limit (mg/kg) : Each 50

Specimen Description:

- 001: Black soft plastic
- 002: Gray soft plastic
- 003: Red soft plastic
- 004: Pink soft plastic
- 005: Cyan soft plastic



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong, China
 Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586



TEST REPORT

No.:SST16000887

Date.:2016-09-24

Page 3 of 4

Result:

Total lead content - California Proposition 65

Test Method: Sample digestion by acid, Analysis was performed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Client's Limit :	100 mg/kg
------------------	-----------

Specimen No.	Result[mg/kg]	Conclusion
001+002	ND	PASS
003+004+005	ND	PASS

Note:

ND = Not detected(<DL)
mg/kg = milligram(s) per kilogram
Detection Limit (mg/kg) : 5

Specimen Description:

- 001: Black soft plastic
- 002: Gray soft plastic
- 003: Red soft plastic
- 004: Pink soft plastic
- 005: Cyan soft plastic



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong, China
Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586



TEST REPORT

No.:SST16000887

Date.:2016-09-24

Page 4 of 4

Photograph of Sample



*** End of Report ***

The test report is considered invalidated without both signature and specialized stamp, The result(s) shown in this test report refer only to the sample(s) tested. Without written approval of SST, this test report shall not be copied except in full .Detailed description are available at the website <http://www.sst-test.com>.



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong,China
Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586